

LOODUSLIKU MATERJALI TERASTIKULINE KOOSTIS GOST-STANDARDI JÄRGI

Jrk nr	Puuraugu nr	Proovi nr	Proovitud intervall, m	Proovi kohaldatud pikkus, m	Kruusa %	Liiva % koos savi ja tolmuga	Osajäägid sõeltel massi %-des												Kokku	Mp	Maavara liik*
							Täisjäägid sõeltel massi %-des														
							70	40	20	10	5	2.5	1.25	0.63	0.315	0.16	0.05	<0.05			
1	Pa-1	1-1	0.3-1.7	1.4	22.8	77.2	0.00	0.00	3.09	11.00	8.72	6.99	8.10	12.33	26.96	10.76	4.48	7.57	100.0	2.2	EL
2		1-2	1.7-2.8	1.1	1.1	98.9	0.00	0.00	3.09	14.09	22.81	29.80	37.90	50.23	77.19	87.95	92.43	100.00	100.0	1.0	TL
Pa-1 kaalutud keskmine				2.5	13.2	86.8	0.00	0.00	1.73	6.16	5.36	4.35	4.97	7.75	22.86	28.90	11.02	6.89	100.0	1.6	EL
							0.00	0.00	1.73	7.89	13.25	17.60	22.57	30.33	53.19	82.09	93.11	100.00			
3	Pa-5	5-1	0.0-1.0	0.6	17.7	82.3	0.00	0.00	0.00	0.00	17.72	5.44	7.82	12.60	25.47	16.20	6.90	7.85	100.0	2.0	EL
							0.00	0.00	0.00	0.00	17.72	23.16	30.98	43.58	69.05	85.25	92.15	100.00			
4	Pa-6	6-1	0.3-1.5	1.2	17.3	82.7	0.00	0.00	0.00	0.00	17.30	7.00	5.90	13.64	26.89	16.03	5.90	7.34	100.0	2.0	EL
							0.00	0.00	0.00	0.00	17.30	24.30	30.20	43.84	70.73	86.76	92.66	100.00			
5	Pa-7	7-1	0.1-1.2	1.1	18.1	81.9	0.00	0.00	0.00	0.00	18.10	7.22	6.92	7.37	29.54	18.81	4.05	7.99	100.0	2.0	EL
6		7-2	1.2-2.5	0.5	1.4	98.6	0.00	0.00	0.00	0.00	18.10	25.32	32.24	39.61	69.15	87.96	92.01	100.00	100.0	1.5	EL
Pa-7 kaalutud keskmine				1.6	12.9	87.1	0.00	0.00	0.00	0.00	1.44	1.06	2.20	5.70	36.10	41.65	5.54	6.31	100.0	1.8	EL
							0.00	0.00	0.00	0.00	1.44	2.50	4.70	10.40	46.50	88.15	93.69	100.00			
							0.00	0.00	0.00	0.00	12.89	5.30	5.45	6.85	31.59	25.95	4.52	7.47	100.0	1.8	EL
							0.00	0.00	0.00	0.00	12.89	18.19	23.63	30.48	62.07	88.02	92.54	100.00			
7	Pa-8	8-1	0.1-2.0	1.9	3.5	96.5	0.00	0.00	0.00	0.00	3.48	4.86	7.98	16.83	50.43	10.70	1.85	3.87	100.0	2.3	EL
8		8-2	2.0-2.6	0.6	20.3	79.7	0.00	0.00	0.00	0.00	3.48	8.34	16.32	33.15	83.58	94.28	96.13	100.00	100.0	2.3	EL
Pa-8 kaalutud keskmine				2.5	7.5	92.5	0.00	0.00	5.66	8.39	6.22	7.49	8.42	15.00	28.28	9.76	3.32	7.46	100.0	2.3	EL
							0.00	0.00	5.66	14.05	20.27	27.76	36.18	51.18	79.46	89.22	92.54	100.00			
							0.00	0.00	1.36	2.01	4.14	5.49	8.09	16.39	45.11	10.47	2.20	4.73	100.0	2.3	EL
							0.00	0.00	1.36	3.37	7.51	13.00	21.09	37.48	82.59	93.07	95.27	100.00			
9	Pa-9	9-1	0.1-0.9	0.8	1.5	98.5	0.00	0.00	0.00	0.00	1.51	3.56	7.50	30.60	43.39	6.31	2.24	4.89	100.0	2.4	EL
10		9-2	0.9-2.0	1.1	18.2	81.8	0.00	0.00	0.00	0.00	1.51	5.07	12.57	43.17	86.56	92.87	95.11	100.00	100.0	2.5	EL
11	Pa-9	9-3	2.0-4.5	0.6	0.6	99.4	0.00	0.00	0.00	0.00	18.21	10.63	10.85	17.08	23.69	8.47	3.80	7.27	100.0	0.8	TL
							0.00	0.00	0.00	0.00	18.21	28.84	39.69	56.77	80.46	88.93	92.73	100.00	100.0	0.8	TL
Pa-9 kaalutud keskmine				2.5	8.6	91.4	0.00	0.00	0.00	0.00	0.57	1.01	0.88	2.54	11.34	45.61	31.45	6.60	100.0	2.0	EL
							0.00	0.00	0.00	0.00	0.57	1.58	2.46	5.00	16.34	61.95	93.40	100.00			
							0.00	0.00	0.00	0.00	8.63	6.06	7.39	17.92	27.03	16.69	9.94	6.35	100.0	2.0	EL
							0.00	0.00	0.00	0.00	8.63	14.69	22.08	39.99	67.02	83.72	93.65	100.00			
12	Pa-13	13-1	0.3-2.3	2.0	8.9	91.1	0.00	0.00	0.00	0.00	8.92	3.21	6.59	23.86	40.59	7.81	2.76	6.26	100.0	2.2	EL
13		13-2	2.3-3.7	1.2	14.4	85.6	0.00	0.00	0.00	0.00	8.92	12.13	18.72	42.58	83.17	90.98	93.74	100.00	100.0	2.1	EL
Pa-13 kaalutud keskmine				3.2	11.0	89.0	0.00	0.00	0.00	0.00	14.44	7.32	7.69	16.14	27.23	12.66	4.80	9.72	100.0	2.2	EL
							0.00	0.00	0.00	0.00	14.44	21.76	29.45	45.59	72.82	85.48	90.28	100.00			
							0.00	0.00	0.00	0.00	10.99	4.75	7.00	20.97	35.58	9.63	3.53	7.56	100.0	2.2	EL
							0.00	0.00	0.00	0.00	10.99	15.74	22.74	43.71	79.29	88.92	92.44	100.00			
14	Pa-14	14-1	0.3-2.8	2.5	20.5	79.5	0.00	0.00	8.69	8.20	3.64	5.00	10.20	17.20	25.49	5.58	4.59	11.41	100.0	2.2	TL
15		14-2	2.8-4.3	1.0	1.1	98.9	0.00	0.00	8.69	16.89	20.53	25.53	35.73	52.93	78.42	84.00	88.59	100.00	100.0	0.6	TL
Pa-14 kaalutud keskmine				3.5	15.0	85.0	0.00	0.00	0.00	0.00	1.09	0.62	0.44	0.98	3.72	47.60	31.71	13.84	100.0	1.7	TL
							0.00	0.00	0.00	0.00	1.09	1.71	2.15	3.13	6.85	54.45	86.16	100.00			
							0.00	0.00	6.21	5.86	2.91	3.75	7.41	12.57	19.27	17.59	12.34	12.10	100.0	1.7	TL
							0.00	0.00	6.21	12.06	14.98	18.72	26.14	38.70	57.97	75.56	87.90	100.00			
16	Pa-15	15-2	0.5-2.0	0.8	1.35	98.65	0.00	0.00	0.00	0.00	1.35	1.40	0.84	1.67	14.19	33.80	25.31	21.44	100.0	0.8	TL
							0.0	0.0	0.0	0.0	1.4	2.8	3.6	5.3	19.5	53.3	78.6	100.0			
17	Pa-16	16-1	0.2-1.1	0.5	11.95	88.05	0.00	0.00	0.00	0.00	11.95	5.64	5.76	8.64	14.93	28.56	15.86	8.66	100.0	1.5	EL
							0.00	0.00	0.00	0.00	11.95	17.59	23.35	31.99	46.92	75.48	91.34	100.00			
Kogu ploki kaalutud keskmine				18.9	11.6	88.4	0.0	0.0	1.6	2.2	7.9	4.9	6.5	13.6	28.3	18.2	8.4	8.4	100.0	1.9	EL
							0.0	0.0	1.6	3.7	11.6	16.5	23.1	36.6	65.0	83.2	91.6	100.0			

Proovide pikkused on kohaldatud vastavalt ploki 1 aT paksusele vasavas punktis (vt Lisa 1).

* Maavara liik: EL Ehitusliiv TL Täiteliiv