

LOODUSLIKU MATERJALI TERASTIKULINE KOOSTIS

| Jrk nr | Puuraugu nr | Proovi nr | Proovitud intervall, m | | Proovi pikkus, m | Kruusa (>5 mm) % | Liiva % koos savi ja tolmu | Osajäägid sõeltel massi %-des | | | | | | | | | | | | Kokku | Liiva peensus moodul | Maavara liik* |
|---|---------------|-----------|--------------------------------|---------|---------------------|------------------------|-------------------------------|-------------------------------|------|------|-------|-----|-----|------|------|-------|------|------|-------|-------|----------------------------|------------------|
| | | | Täisjäägid sõeltel massi %-des | | | | | | | | | | | | | | | | | | | |
| | | | alates, m | kuni, m | | | | >70 | 40 | 20 | 10 | 5 | 2.5 | 1.25 | 0.63 | 0.315 | 0.16 | 0.05 | <0.05 | | | |
| 1 | Puurauk nr 1 | 1 | 2.7 | 6.5 | 3.8 | 0.9 | 99.1 | 0.0 | 0.0 | 0.0 | 0.6 | 0.3 | 0.2 | 0.3 | 0.3 | 27.0 | 49.0 | 15.3 | 7.0 | 100.0 | 1.1 | TL |
| 2 | Puurauk nr 2 | 2 | 0.3 | 5.5 | 5.2 | 0.0 | 100.0 | 0.0 | 0.0 | 0.0 | 0.6 | 0.9 | 1.1 | 1.4 | 1.7 | 28.7 | 77.7 | 93.0 | 100.0 | 100.0 | 1.0 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 1.5 | 28.0 | 69.9 | 89.7 | 100.0 | | | |
| 3 | Puurauk nr 3 | 3 | 0.3 | 3.5 | 3.2 | 0.1 | 99.9 | 0.0 | 0.0 | 0.0 | 0.1 | 0.0 | 0.0 | 0.4 | 8.1 | 17.7 | 31.0 | 36.9 | 5.8 | 100.0 | 0.9 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.1 | 0.5 | 8.6 | 26.3 | 57.3 | 94.2 | 100.0 | | | |
| 4 | Puurauk nr 4 | 4 | 0.5 | 4.2 | 3.7 | 0.1 | 99.9 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.0 | 0.2 | 3.3 | 31.6 | 44.8 | 13.9 | 6.1 | 100.0 | 1.2 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.3 | 3.6 | 35.2 | 80.0 | 93.9 | 100.0 | | | |
| 5 | Puurauk nr 5 | 5 | 0.4 | 4.1 | 3.7 | 0.0 | 100.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 1.8 | 54.2 | 35.0 | 6.0 | 3.0 | 100.0 | 1.5 | EL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 1.8 | 56.0 | 91.0 | 97.0 | 100.0 | | | |
| 6 | Puurauk nr 8 | 8 | 0.3 | 4.8 | 4.5 | 0.2 | 99.8 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.1 | 0.9 | 6.1 | 18.0 | 21.4 | 44.6 | 8.7 | 100.0 | 0.8 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.1 | 0.2 | 0.3 | 1.2 | 7.3 | 25.3 | 46.7 | 91.3 | 100.0 | | | |
| 7 | Puurauk nr 8 | 8 | 4.8 | 6.2 | 1.4 | 0.2 | 99.8 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.1 | 0.9 | 6.1 | 18.0 | 21.4 | 44.6 | 8.7 | 100.0 | 0.8 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.1 | 0.2 | 0.3 | 1.2 | 7.3 | 25.3 | 46.7 | 91.3 | 100.0 | | | |
| 8 | Puurauk nr 9 | 9 | 0.2 | 6.5 | 6.3 | 0.1 | 99.9 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.0 | 0.2 | 0.8 | 12.4 | 35.3 | 45.2 | 6.0 | 100.0 | 0.6 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.3 | 1.1 | 13.5 | 48.8 | 94.0 | 100.0 | | | |
| 9 | Puurauk nr 9 | 9 | 6.5 | 6.7 | 0.2 | 0.1 | 99.9 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.0 | 0.2 | 0.8 | 12.4 | 35.3 | 45.2 | 6.0 | 100.0 | 0.6 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.3 | 1.1 | 13.5 | 48.8 | 94.0 | 100.0 | | | |
| 10 | Puurauk nr 10 | 10 | 0.4 | 3.2 | 2.8 | 0.0 | 100.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.8 | 19.2 | 36.6 | 20.7 | 16.8 | 5.8 | 100.0 | 1.6 | EL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.9 | 20.1 | 56.7 | 77.4 | 94.2 | 100.0 | | | |
| 11 | Puurauk nr 10 | 10 | 3.2 | 4.8 | 1.6 | 0.0 | 100.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.8 | 19.2 | 36.6 | 20.7 | 16.8 | 5.8 | 100.0 | 1.6 | EL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.9 | 20.1 | 56.7 | 77.4 | 94.2 | 100.0 | | | |
| 12 | Puurauk nr 12 | 12 | 0.3 | 3.5 | 3.2 | 0.0 | 100.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.4 | 13.1 | 25.2 | 53.9 | 7.4 | 100.0 | 0.5 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.0 | 0.4 | 13.5 | 38.7 | 92.6 | 100.0 | | | |
| | | 13 | 3.5 | 6.2 | 2.7 | 0.1 | 99.9 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.0 | 0.0 | 0.4 | 16.6 | 31.8 | 46.0 | 5.1 | 100.0 | 0.7 | TL |
| | | | | | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.1 | 0.5 | 17.1 | 48.9 | 94.9 | 100.0 | | | |
| Kogu uuringuruumi kaalutud keskmised omadused | | | | | 42.3 | 0.1 | 99.9 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.0 | 0.3 | 4.3 | 24.8 | 33.4 | 30.3 | 6.8 | 100.0 | 1.0 | TL |
| 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.2 | 0.5 | 4.8 | 29.6 | 63.0 | 93.2 | 100.0 | | | | | | | | | | | |

| | | | | | | | | | | | | | | | | |
|---|------|-----|------|-----|-----|-----|-----|-----|-----|-----|------|------|------|------|-------|-------|
| Ploki 3 kaalutud keskmised omadused (veepealne plokk) | 39.1 | 0.2 | 99.8 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.0 | 0.3 | 3.6 | 24.6 | 34.3 | 30.2 | 6.7 | 100.0 |
| | | | | 0.0 | 0.0 | 0.0 | 0.1 | 0.2 | 0.2 | 0.5 | 4.1 | 28.7 | 63.0 | 93.3 | 100.0 | |
| Ploki 5 kaalutud keskmised omadused (veealune plokk) | 3.2 | 0.1 | 99.9 | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.1 | 0.8 | 12.3 | 27.0 | 21.9 | 30.7 | 7.1 | 100.0 |
| | | | | 0.0 | 0.0 | 0.0 | 0.0 | 0.1 | 0.2 | 1.0 | 13.3 | 40.3 | 62.2 | 92.9 | 100.0 | |

* Maavara liik TL Täiteliiv EL Ehitusliiv

* Kvaliteedi hindamisel on kasutatud vaid nende puuraukude andmeid, mis varu arvutuse plokiga kattuvad.