

Kruusa ja liiva fraktsioonide sisaldus looduslikus materjalis

Jrk nr	Uuringupunkti nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruusa sisaldus proovis, %	Liiva sisaldus proovis, %	Sõela osajäägid, %																	Maavara liik***	
			alates	kuni				125	80	63	40	31.5	20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063		< 0.063
Põhjapoolne ala																										
1	K/Pa-1	1-1	1.0	3.0	2.0	0.0	100.0	0.00	0.00	0.00	0.00	0.00	5.94	0.00	8.39	11.94	4.36	5.97	12.14	7.10	10.04	20.41	10.90	1.00	1.81	EL
2		1-2	3.0	5.2	2.2	0.0	100.0	0.00	0.00	0.00	0.00	0.00	6.21	0.00	2.38	3.28	2.32	4.13	5.05	5.05	9.99	36.44	23.36	0.80	0.99	EL
3		1-3	5.2	7.5	2.3	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.12	0.12	0.43	0.36	0.97	3.57	15.50	64.04	13.44	1.45	EL
4	K/Pa-13	13-1	0.4	3.0	2.6	7.6	92.4	0.00	0.00	0.00	0.00	7.59	18.58	3.01	8.54	7.18	3.48	5.68	5.41	5.21	7.09	18.20	8.09	0.65	1.29	EL
5		13-2	3.0	5.1	2.1	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.83	0.39	0.74	1.10	0.92	2.85	1.27	1.75	4.44	35.39	45.46	2.88	1.98	EL
6	K/Pa-14	14-1	0.5	2.0	1.5	3.3	96.7	0.00	0.00	0.00	0.00	3.27	33.87	3.02	4.61	7.16	3.10	4.53	4.18	4.34	6.75	15.47	7.08	0.64	1.98	EL
7		14-2	2.0	4.7	2.7	0.0	100.0	0.00	0.00	0.00	0.00	0.00	6.61	0.00	1.16	1.68	0.57	2.47	1.87	3.27	7.40	38.26	33.45	1.55	1.71	EL
8		14-3	4.7	7.5	2.8	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.10	0.07	0.40	0.27	0.72	2.72	29.39	56.38	6.05	3.90	EL
9	Pa-13	37	0.3	3.2	2.9	12.2	87.8	0.00	2.60	0.90	1.40	7.25	13.79	3.20	3.54	6.24	3.25	4.70	4.62	4.70	7.58	11.87	9.60	1.89	7.60	TL
10		38	3.2	4.1	0.9	1.7	98.3	0.00	0.00	0.00	0.00	1.74	3.31	2.65	2.93	4.34	1.81	2.86	3.77	5.65	13.05	25.46	22.21	3.24	7.00	TL
11		39**	4.1	8.4	4.3	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.10	0.11	0.38	0.77	0.91	4.26	22.20	51.07	14.44	5.76	TL
12	Pa-20*	40	0.5	4.0	3.5	19.5	80.5	0.00	1.92	4.88	7.59	5.10	9.69	5.68	6.28	8.64	3.17	3.91	3.17	4.74	7.30	10.61	13.94	2.94	0.45	EL
13		41	4.0	9.0	5.0	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.48	0.52	0.69	0.64	1.25	6.26	31.55	50.33	5.73	2.56	EL
Plokk 30 ja 31 aT kaalutud keskmised näitajad (ainult usaldusväärsete proovide andmete alusel)					30.5	4.3	95.7	0.0	0.5	0.6	1.0	2.1	7.3	1.5	3.0	4.0	1.8	3.0	3.2	3.4	6.8	24.2	31.0	3.7	2.6	EL
Lõunapoolne ala																										
1	K/Pa-1	1-1	1.0	3.0	2.0	0.0	100.0	0.00	0.00	0.00	0.00	0.00	5.94	0.00	8.39	11.94	4.36	5.97	12.14	7.10	10.04	20.41	10.90	1.00	1.81	EL
2		1-2	3.0	5.2	2.2	0.0	100.0	0.00	0.00	0.00	0.00	0.00	6.21	0.00	2.38	3.28	2.32	4.13	5.05	5.05	9.99	36.44	23.36	0.80	0.99	EL
3		1-3	5.2	7.5	2.3	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.12	0.12	0.43	0.36	0.97	3.57	15.50	64.04	13.44	1.45	EL
4	K/Pa-2	2-1	0.5	4.7	4.2	0.0	100.0	0.00	0.00	0.00	0.00	0.00	2.27	0.00	0.00	0.57	0.06	0.27	0.43	0.78	3.20	32.32	51.72	5.32	3.06	EL
5		2-2	4.7	7.0	2.3	1.0	99.0	0.00	0.00	0.00	0.00	1.00	2.00	2.00	2.00	3.00	1.00	3.00	4.00	5.00	13.00	42.00	21.00	0.50	0.50	EL
6	K/Pa-3	3-1	1.0	2.8	1.8	0.0	100.0	0.00	0.00	0.00	0.00	0.00	4.77	0.95	1.00	1.63	0.60	1.57	1.27	2.34	7.76	37.59	34.31	2.39	3.82	EL
7		3-2	2.8	6.0	3.2	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.34	0.03	0.28	0.14	0.58	3.73	27.45	57.37	7.99	2.09	EL
8	K/Pa-7	7-1	1.0	2.5	1.5	3.8	96.2	0.00	0.00	0.00	0.00	3.83	7.90	0.86	2.76	4.41	1.58	1.46	3.04	4.55	10.36	33.67	17.39	1.80	6.39	TL
9		7-2	2.5	5.5	3.0	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	1.00	0.00	2.00	30.00	59.00	6.50	1.50	EL
10	Pa-13	37	0.3	3.2	2.9	12.2	87.8	0.00	2.60	0.90	1.40	7.25	13.79	3.20	3.54	6.24	3.25	4.70	4.62	4.70	7.58	11.87	9.60	1.89	7.60	TL
11		38	3.2	4.1	0.9	1.7	98.3	0.00	0.00	0.00	0.00	1.74	3.31	2.65	2.93	4.34	1.81	2.86	3.77	5.65	13.05	25.46	22.21	3.24	7.00	TL
12		39**	4.1	8.4	4.3	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.10	0.11	0.38	0.77	0.91	4.26	22.20	51.07	14.44	5.76	TL
13	Pa-27*	53	0.8	4.5	3.7	16.1	83.9	0.00	1.01	3.78	5.88	5.43	10.33	4.50	4.98	7.91	3.66	3.99	1.66	2.84	6.56	15.98	17.26	1.42	2.83	EL
14		54	4.5	6.0	1.5	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.55	0.59	0.91	1.40	3.19	8.56	29.11	46.29	6.58	2.83	EL
Plokk 32 ja 33 aT kaalutud keskmised näitajad (ainult usaldusväärsete proovide andmete alusel)					31.5	3.3	96.7	0.0	0.4	0.5	0.8	1.6	4.5	1.1	2.0	3.3	1.4	2.2	2.6	2.8	6.7	26.8	35.4	4.2	3.0	EL

** Ebausaldusväärne proov
*** Maavara liik: EL - ehitusliiv, TL - täiteliiv