

KIVIMI FÜÜSIKALIS-MEHAANILISED OMADUSED

Jrk nr	Proovi number	Proovi võtmise koht	Proovi intervall, m			Kaalukadu Los Angelese katsel, %	Kaalukadu külmakindluse katsel, %
			alates	kuni	pikkus		
2025. a uuring							
1	LA-F1	PA1-25	0.30	2.55	2.25	39	0.7
2	LA-F2	PA1-25	2.55	5.00	2.45	29	1.8
2021.a uuring							
3	Pa-3-21-1	Pa-3-21	0.85	5.40	4.55	36	1.0
4	Pa-3-21-2	Pa-3-21	2.30	5.40	3.10	37	0.5
5	Pa-3-21-3	Pa-3-21	5.40	10.00	4.60	31	2.7
6	Pa-4-21-1	Pa-4-21	0.70	4.70	4.00	34	0.8
7	Pa-4-21-2	Pa-4-21	4.70	10.50	5.80	37	0.4
Kogu uuritud materjali kaalutud keskmised:					26.75	34.8	1.1
Ploki 7 aT kivimi kaalutud keskmised:					13.90	36.1	0.8
Ploki 9 aT kivimi kaalutud keskmised:					12.85	33.3	1.5