

## KIVIMI KEEMILINE KOOSTIS

Jrk nr	Proovi number	Proovi võtmise koht	Proovi intervall, m			Karbonaatanalüüsi tulemused (EVS-EN 196-2:2013)		
			alates	kuni	pikkus	CaO, %	MgO, %	Lahustu matu jääk, %
2025. a uuring								
1	K1	PA1-25	0.30	2.55	2.25	29.07	16.67	11.35
2	K2	PA1-25	2.55	5.00	2.45	47.11	4.70	7.54
3	K3	PA2-25	0.00	1.50	1.50	29.30	16.80	10.58
4	K4	PA2-25	1.50	4.00	2.50	47.06	3.73	8.03
1980. a uuring								
6	1	Pa-14	1.20	4.50	3.30	29.85	18.21	8.46
7	2	Pa-14	4.50	7.80	3.30	29.62	17.06	11.40
Kogu uuritud materjali kaalutud keskmised:					15.30	35.21	13.07	9.51
Ploki 7 aT kivimi kaalutud keskmised:					7.05	29.48	17.42	9.83
Ploki 9 aT kivimi kaalutud keskmised:					8.25	40.10	9.35	9.23