

LOODUSLIKUST MATERJALIST VÄLJA SÕELUTUD LIIVA OMADUSED

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuaga, %	Täisjäägid sõeltel (mm), % kogu proovist													Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %
			Osajäägid sõeltel (mm), % kogu proovist																			
			Alates	Kuni				20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063	<0,063		
1	K02	K02-01	0.20	1.50	1.30	1.0	99.0	7.1	11.1	14.1	18.2	20.2	24.2	29.3	46.5	69.7	85.9	89.9	91.6	100.0	100.0	8.4
								7.1	4.0	3.0	4.0	2.0	4.0	5.1	17.2	23.2	16.2	4.0	1.7	8.4		
2	K02	K02-02	3.25	5.25	2.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	39.0	83.2	100.0	100.0	16.8
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	38.0	44.2	16.8		
3	K02	K02-03	5.25	6.10	0.85	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	8.0	67.0	89.0	100.0	100.0	11.0
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	8.0	59.0	22.0	11.0		
4	K03	K03-01*	0.20	0.70	0.50	0.0	100.0	0.0	1.0	1.0	2.0	3.0	4.0	7.0	13.0	22.0	43.0	66.0	79.5	100.0	100.0	20.5
								0.0	1.0	0.0	1.0	1.0	1.0	3.0	6.0	9.0	21.0	23.0	13.5	20.5		
5	K03	K03-02	0.70	2.00	1.30	12.0	88.0	9.1	14.8	19.3	27.3	29.5	35.2	43.2	59.1	70.5	78.4	86.4	90.9	100.0	100.0	9.1
								9.1	5.7	4.5	8.0	2.3	5.7	8.0	15.9	11.4	8.0	8.0	4.5	9.1		
6	K03	K03-03	2.00	5.10	3.10	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	7.0	62.0	89.1	100.0	100.0	10.9
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	7.0	55.0	27.1	10.9		
7	K04	K04-01	1.30	2.60	1.30	3.0	97.0	12.4	17.5	22.7	29.9	32.0	36.1	41.2	55.7	67.0	77.3	83.5	88.1	100.0	100.0	11.9
								12.4	5.2	5.2	7.2	2.1	4.1	5.2	14.4	11.3	10.3	6.2	4.6	11.9		
8	K04	K04-02*	2.60	3.60	1.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	9.0	45.0	100.0	100.0	55.0
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	9.0	36.0	55.0		
9	K06	K06-01	0.30	1.30	1.00	2.0	98.0	0.0	2.0	3.1	5.1	6.1	8.2	11.2	20.4	37.8	65.3	87.8	92.9	100.0	100.0	7.1
								0.0	2.0	1.0	2.0	1.0	2.0	3.1	9.2	17.3	27.6	22.4	5.1	7.1		
10	K06	K06-02	1.30	3.00	1.70	15.0	85.0	12.9	16.5	21.2	29.4	32.9	38.8	50.6	63.5	72.9	81.2	87.1	88.7	100.0	100.0	11.3
								12.9	3.5	4.7	8.2	3.5	5.9	11.8	12.9	9.4	8.2	5.9	1.6	11.3		
11	K06	K06-03	3.00	4.00	1.00	0.0	100.0	1.0	2.0	2.0	2.0	2.0	3.0	5.0	7.0	12.0	49.0	92.0	96.8	100.0	100.0	3.2
								1.0	1.0	0.0	0.0	0.0	1.0	2.0	2.0	5.0	37.0	43.0	4.8	3.2		
12	PA01a	PA01a-01	0.60	2.60	2.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	13.0	72.0	93.6	100.0	100.0	6.4
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	12.0	59.0	21.6	6.4		
13	PA01a	PA01a-02	3.50	4.20	0.70	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	59.0	89.8	100.0	100.0	10.2
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	58.0	30.8	10.2		
14	PA01a	PA01a-03	5.10	7.10	2.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	2.0	33.0	71.3	100.0	100.0	28.7
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	1.0	31.0	38.3	28.7		
15	PA01a	PA01a-04	7.10	9.10	2.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	1.0	3.0	34.0	72.1	100.0	100.0	27.9
								0.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	0.0	2.0	31.0	38.1	27.9		
16	PA01a	PA01a-05	9.10	10.40	1.30	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	3.0	46.0	78.8	100.0	100.0	21.2
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	2.0	43.0	32.8	21.2		
17	PA02	PA02-01	1.40	2.20	0.80	1.0	99.0	0.0	1.0	2.0	3.0	3.0	5.1	7.1	14.1	32.3	73.7	96.0	98.1	100.0	100.0	1.9
								0.0	1.0	1.0	1.0	0.0	2.0	2.0	7.1	18.2	41.4	22.2	2.1	1.9		
18	PA02	PA02-02	2.20	4.00	1.80	0.0	100.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	4.0	24.0	82.0	95.0	96.4	100.0	100.0	3.6
								0.0	0.0	0.0	0.0	0.0	1.0	0.0	3.0	20.0	58.0	13.0	1.4	3.6		
19	PA02	PA02-03	4.00	5.00	1.00	2.0	98.0	1.0	3.1	4.1	9.2	12.2	17.3	24.5	33.7	49.0	80.6	93.9	96.5	100.0	100.0	3.5
								1.0	2.0	1.0	5.1	3.1	5.1	7.1	9.2	15.3	31.6	13.3	2.7	3.5		
20	PA02	PA02-04	5.00	5.07	0.07	0.0	100.0	4.0	7.0	10.0	18.0	22.0	28.0	36.0	45.0	61.0	78.0	86.0	89.8	100.0	100.0	10.2
								4.0	3.0	3.0	8.0	4.0	6.0	8.0	9.0	16.0	17.0	8.0	3.8	10.2		
20	PA02	PA02-04	5.07	6.70	1.63	0.0	100.0	4.0	7.0	10.0	18.0	22.0	28.0	36.0	45.0	61.0	78.0	86.0	89.8	100.0	100.0	10.2
								4.0	3.0	3.0	8.0	4.0	6.0	8.0	9.0	16.0	17.0	8.0	3.8	10.2		
21	PA02	PA02-05	6.70	9.70	3.00	0.0	100.0	1.0	2.0	3.0	6.0	8.0	11.0	17.0	26.0	41.0	66.0	82.0	88.6	100.0	100.0	11.4
								1.0	1.0	1.0	3.0	2.0	3.0	6.0	9.0	15.0	25.0	16.0	6.6	11.4		
22	PA02	PA02-06	9.70	11.70	2.00	0.0	100.0	0.0	0.0	1.0	2.0	3.0	5.0	10.0	20.0	37.0	63.0	81.0	87.4	100.0	100.0	12.6
								0.0	0.0	1.0	1.0	1.0	2.0	5.0	10.0	17.0	26.0	18.0	6.4	12.6		

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuaga, %	Täisjäägid sõeltel (mm), % kogu proovist												Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %	
			Osajäägid sõeltel (mm), % kogu proovist																			
			Alates	Kuni				20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063			<0,063
23	PA02	PA02-07	11.70	13.70	2.00	0.0	100.0	0.0	0.0	1.0	4.0	5.0	9.0	15.0	24.0	39.0	62.0	82.0	88.6	100.0	100.0	11.4
								0.0	0.0	1.0	3.0	1.0	4.0	6.0	9.0	15.0	23.0	20.0	6.6	11.4		
24	PA02	PA02-08	13.70	15.00	1.30	0.0	100.0	1.0	3.0	5.0	8.0	11.0	15.0	21.0	32.0	49.0	73.0	88.0	92.3	100.0	100.0	7.7
								1.0	2.0	2.0	3.0	3.0	4.0	6.0	11.0	17.0	24.0	15.0	4.3	7.7		
25	PA03	PA03-01	0.40	2.00	1.60	0.0	100.0	3.0	7.0	10.0	17.0	22.0	27.0	34.0	43.0	56.0	72.0	84.0	88.1	100.0	100.0	11.9
								3.0	4.0	3.0	7.0	5.0	5.0	7.0	9.0	13.0	16.0	12.0	4.1	11.9		
26	PA03	PA03-02	2.00	4.00	2.00	12.0	88.0	9.1	13.6	19.3	27.3	31.8	39.8	48.9	60.2	72.7	88.6	96.6	98.6	100.0	100.0	1.4
								9.1	4.5	5.7	8.0	4.5	8.0	9.1	11.4	12.5	15.9	8.0	2.0	1.4		
27	PA03	PA03-03	4.00	4.17	0.17	0.0	100.0	1.0	2.0	4.0	8.0	10.0	14.0	19.0	27.0	38.0	57.0	78.0	84.8	100.0	100.0	15.2
								1.0	1.0	2.0	4.0	2.0	4.0	5.0	8.0	11.0	19.0	21.0	6.8	15.2		
27	PA03	PA03-03	4.17	6.00	1.83	0.0	100.0	1.0	2.0	4.0	8.0	10.0	14.0	19.0	27.0	38.0	57.0	78.0	84.8	100.0	100.0	15.2
								1.0	1.0	2.0	4.0	2.0	4.0	5.0	8.0	11.0	19.0	21.0	6.8	15.2		
28	PA03	PA03-04	6.00	8.00	2.00	0.0	100.0	2.0	6.0	10.0	22.0	26.0	33.0	43.0	52.0	63.0	78.0	87.0	90.8	100.0	100.0	9.2
								2.0	4.0	4.0	12.0	4.0	7.0	10.0	9.0	11.0	15.0	9.0	3.8	9.2		
29	PA03	PA03-05	8.00	9.00	1.00	0.0	100.0	2.0	3.0	6.0	11.0	14.0	21.0	31.0	42.0	55.0	72.0	85.0	88.5	100.0	100.0	11.5
								2.0	1.0	3.0	5.0	3.0	7.0	10.0	11.0	13.0	17.0	13.0	3.5	11.5		
30	PA03	PA03-06	9.00	11.00	2.00	0.0	100.0	0.0	1.0	1.0	3.0	4.0	7.0	12.0	22.0	37.0	60.0	81.0	87.7	100.0	100.0	12.3
								0.0	1.0	0.0	2.0	1.0	3.0	5.0	10.0	15.0	23.0	21.0	6.7	12.3		
31	PA03	PA03-07	11.00	13.00	2.00	0.0	100.0	0.0	1.0	1.0	2.0	4.0	7.0	13.0	23.0	39.0	64.0	83.0	88.6	100.0	100.0	11.4
								0.0	1.0	0.0	1.0	2.0	3.0	6.0	10.0	16.0	25.0	19.0	5.6	11.4		
32	PA03	PA03-08	13.00	15.00	2.00	0.0	100.0	1.0	1.0	2.0	5.0	6.0	9.0	15.0	24.0	37.0	60.0	82.0	88.8	100.0	100.0	11.2
								1.0	0.0	1.0	3.0	1.0	3.0	6.0	9.0	13.0	23.0	22.0	6.8	11.2		
33	PA04	PA04-01	0.50	2.93	2.43	1.0	99.0	1.0	1.0	3.0	5.1	6.1	9.1	13.1	22.2	37.4	64.6	89.9	96.9	100.0	100.0	3.1
								1.0	0.0	2.0	2.0	1.0	3.0	4.0	9.1	15.2	27.3	25.3	7.0	3.1		
33	PA04	PA04-01	2.93	3.00	0.07	1.0	99.0	1.0	1.0	3.0	5.1	6.1	9.1	13.1	22.2	37.4	64.6	89.9	96.9	100.0	100.0	3.1
								1.0	0.0	2.0	2.0	1.0	3.0	4.0	9.1	15.2	27.3	25.3	7.0	3.1		
34	PA04	PA04-02	3.00	5.00	2.00	0.0	100.0	2.0	3.0	4.0	7.0	8.0	12.0	17.0	26.0	38.0	62.0	86.0	96.0	100.0	100.0	4.0
								2.0	1.0	1.0	3.0	1.0	4.0	5.0	9.0	12.0	24.0	24.0	10.0	4.0		
35	PA04	PA04-03	5.00	7.00	2.00	0.0	100.0	0.0	0.0	0.0	0.0	1.0	2.0	4.0	9.0	22.0	51.0	79.0	88.4	100.0	100.0	11.6
								0.0	0.0	0.0	0.0	1.0	1.0	2.0	5.0	13.0	29.0	28.0	9.4	11.6		
36	PA04	PA04-04	7.00	9.00	2.00	0.0	100.0	0.0	0.0	0.0	0.0	1.0	1.0	2.0	6.0	18.0	46.0	81.0	88.4	100.0	100.0	11.6
								0.0	0.0	0.0	0.0	1.0	0.0	1.0	4.0	12.0	28.0	35.0	7.4	11.6		
37	PA04	PA04-05	9.00	11.00	2.00	0.0	100.0	0.0	0.0	0.0	0.0	1.0	1.0	2.0	4.0	8.0	35.0	62.0	82.5	100.0	100.0	17.5
								0.0	0.0	0.0	0.0	1.0	0.0	1.0	2.0	4.0	27.0	27.0	20.5	17.5		
38	PA04	PA04-06	11.00	13.00	2.00	0.0	100.0	0.0	0.0	1.0	4.0	6.0	10.0	13.0	16.0	18.0	32.0	71.0	86.7	100.0	100.0	13.3
								0.0	0.0	1.0	3.0	2.0	4.0	3.0	3.0	2.0	14.0	39.0	15.7	13.3		
39	PA04	PA04-07	13.00	15.00	2.00	0.0	100.0	0.0	0.0	0.0	1.0	2.0	3.0	7.0	14.0	26.0	56.0	81.0	90.2	100.0	100.0	9.8
								0.0	0.0	0.0	1.0	1.0	1.0	4.0	7.0	12.0	30.0	25.0	9.2	9.8		
40	PA05	PA05-01	1.20	2.24	1.04	0.0	100.0	0.0	2.0	3.0	8.0	10.0	14.0	19.0	28.0	41.0	62.0	78.0	84.5	100.0	100.0	15.5
								0.0	2.0	1.0	5.0	2.0	4.0	5.0	9.0	13.0	21.0	16.0	6.5	15.5		
40	PA05	PA05-01	2.24	3.20	0.96	0.0	100.0	0.0	2.0	3.0	8.0	10.0	14.0	19.0	28.0	41.0	62.0	78.0	84.5	100.0	100.0	15.5
								0.0	2.0	1.0	5.0	2.0	4.0	5.0	9.0	13.0	21.0	16.0	6.5	15.5		
41	PA05	PA05-02	3.20	5.00	1.80	0.0	100.0	0.0	0.0	2.0	5.0	6.0	9.0	13.0	20.0	34.0	57.0	78.0	85.8	100.0	100.0	14.2
								0.0	0.0	2.0	3.0	1.0	3.0	4.0	7.0	14.0	23.0	21.0	7.8	14.2		
42	PA05	PA05-03	5.00	7.00	2.00	0.0	100.0	0.0	1.0	1.0	3.0	4.0	5.0	8.0	13.0	27.0	56.0	80.0	87.1	100.0	100.0	12.9
								0.0	1.0	0.0	2.0	1.0	1.0	3.0	5.0	14.0	29.0	24.0	7.1	12.9		
43	PA05	PA05-04	7.00	9.00	2.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	1.0	2.0	7.0	24.0	66.0	86.0	90.4	100.0	100.0	9.6
								0.0	0.0	0.0	0.0	0.0	1.0	1.0	5.0	17.0	42.0	20.0	4.4	9.6		

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuaga, %	Täisjäägid sõeltel (mm), % kogu proovist													Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %
			Osajäägid sõeltel (mm), % kogu proovist																			
			Alates	Kuni				20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063	<0,063		
44	PA05	PA05-05	9.00	11.00	2.00	0.0	100.0	0.0	0.0	0.0	1.0	1.0	2.0	5.0	8.0	16.0	47.0	84.0	91.1	100.0	100.0	8.9
								0.0	0.0	0.0	1.0	0.0	1.0	3.0	3.0	8.0	31.0	37.0	7.1	8.9		
45	PA05	PA05-06	11.00	13.00	2.00	0.0	100.0	0.0	0.0	1.0	1.0	1.0	2.0	2.0	4.0	9.0	21.0	52.0	82.3	100.0	100.0	17.7
								0.0	0.0	1.0	0.0	0.0	1.0	0.0	2.0	5.0	12.0	31.0	30.3	17.7		
46	PA05	PA05-07	13.00	14.00	1.00	0.0	100.0	1.0	2.0	3.0	7.0	8.0	10.0	13.0	17.0	22.0	36.0	64.0	84.6	100.0	100.0	15.4
								1.0	1.0	1.0	4.0	1.0	2.0	3.0	4.0	5.0	14.0	28.0	20.6	15.4		
47	PA06	PA06-01	0.50	2.50	2.00	5.0	95.0	10.5	14.7	20.0	28.4	30.5	36.8	46.3	58.9	73.7	86.3	91.6	93.4	100.0	100.0	6.6
								10.5	4.2	5.3	8.4	2.1	6.3	9.5	12.6	14.7	12.6	5.3	1.8	6.6		
48	PA06	PA06-02	2.50	2.53	0.03	6.0	94.0	7.4	11.7	16.0	22.3	25.5	29.8	36.2	45.7	58.5	77.7	89.4	93.9	100.0	100.0	6.1
								7.4	4.3	4.3	6.4	3.2	4.3	6.4	9.6	12.8	19.1	11.7	4.6	6.1		
48	PA06	PA06-02	2.53	4.50	1.97	6.0	94.0	7.4	11.7	16.0	22.3	25.5	29.8	36.2	45.7	58.5	77.7	89.4	93.9	100.0	100.0	6.1
								7.4	4.3	4.3	6.4	3.2	4.3	6.4	9.6	12.8	19.1	11.7	4.6	6.1		
49	PA06	PA06-03	4.50	6.50	2.00	0.0	100.0	0.0	1.0	4.0	9.0	12.0	16.0	21.0	30.0	46.0	71.0	84.0	87.9	100.0	100.0	12.1
								0.0	1.0	3.0	5.0	3.0	4.0	5.0	9.0	16.0	25.0	13.0	3.9	12.1		
50	PA06	PA06-04	6.50	8.50	2.00	0.0	100.0	1.0	2.0	3.0	4.0	5.0	8.0	11.0	17.0	28.0	52.0	78.0	86.2	100.0	100.0	13.8
								1.0	1.0	1.0	1.0	1.0	3.0	3.0	6.0	11.0	24.0	26.0	8.2	13.8		
51	PA06	PA06-05	8.50	10.50	2.00	0.0	100.0	1.0	3.0	4.0	7.0	10.0	14.0	20.0	31.0	45.0	65.0	85.0	91.7	100.0	100.0	8.3
								1.0	2.0	1.0	3.0	3.0	4.0	6.0	11.0	14.0	20.0	20.0	6.7	8.3		
52	PA06	PA06-06	10.50	12.50	2.00	0.0	100.0	0.0	1.0	1.0	2.0	3.0	4.0	8.0	16.0	26.0	55.0	83.0	90.5	100.0	100.0	9.5
								0.0	1.0	0.0	1.0	1.0	1.0	4.0	8.0	10.0	29.0	28.0	7.5	9.5		
53	PA06	PA06-07	12.50	15.00	2.50	0.0	100.0	0.0	0.0	0.0	1.0	1.0	2.0	4.0	8.0	15.0	36.0	71.0	88.1	100.0	100.0	11.9
								0.0	0.0	0.0	1.0	0.0	1.0	2.0	4.0	7.0	21.0	35.0	17.1	11.9		
54	PA07	PA07-01	0.40	2.00	1.60	1.0	99.0	4.0	7.1	10.1	17.2	20.2	26.3	33.3	42.4	52.5	65.7	76.8	82.0	100.0	100.0	18.0
								4.0	3.0	3.0	7.1	3.0	6.1	7.1	9.1	10.1	13.1	11.1	5.3	18.0		
55	PA07	PA07-02	2.00	3.04	1.04	0.0	100.0	1.0	2.0	4.0	9.0	11.0	16.0	24.0	37.0	54.0	71.0	80.0	85.2	100.0	100.0	14.8
								1.0	1.0	2.0	5.0	2.0	5.0	8.0	13.0	17.0	17.0	9.0	5.2	14.8		
55	PA07	PA07-02	3.04	4.00	0.96	0.0	100.0	1.0	2.0	4.0	9.0	11.0	16.0	24.0	37.0	54.0	71.0	80.0	85.2	100.0	100.0	14.8
								1.0	1.0	2.0	5.0	2.0	5.0	8.0	13.0	17.0	17.0	9.0	5.2	14.8		
56	PA07	PA07-03	4.00	6.00	2.00	0.0	100.0	1.0	2.0	6.0	13.0	16.0	23.0	30.0	44.0	64.0	79.0	85.0	88.4	100.0	100.0	11.6
								1.0	1.0	4.0	7.0	3.0	7.0	7.0	14.0	20.0	15.0	6.0	3.4	11.6		
57	PA07	PA07-04	6.00	8.00	2.00	1.0	99.0	2.0	7.1	11.1	20.2	24.2	29.3	37.4	47.5	60.6	73.7	81.8	87.1	100.0	100.0	12.9
								2.0	5.1	4.0	9.1	4.0	5.1	8.1	10.1	13.1	13.1	8.1	5.3	12.9		
58	PA07	PA07-05	8.00	10.00	2.00	0.0	100.0	2.0	4.0	6.0	11.0	13.0	17.0	23.0	30.0	41.0	55.0	71.0	81.1	100.0	100.0	18.9
								2.0	2.0	2.0	5.0	2.0	4.0	6.0	7.0	11.0	14.0	16.0	10.1	18.9		
59	PA07	PA07-06	10.00	11.60	1.60	1.0	99.0	1.0	2.0	2.0	6.1	9.1	14.1	20.2	31.3	48.5	68.7	82.8	89.4	100.0	100.0	10.6
								1.0	1.0	0.0	4.0	3.0	5.1	6.1	11.1	17.2	20.2	14.1	6.6	10.6		
60	PA08	PA08-01	0.85	1.70	0.85	25.0	75.0	17.3	24.0	29.3	40.0	44.0	50.7	57.3	68.0	81.3	92.0	96.0	96.7	100.0	100.0	3.3
								17.3	6.7	5.3	10.7	4.0	6.7	6.7	10.7	13.3	10.7	4.0	0.7	3.3		
61	PA08	PA08-02	1.70	3.15	1.45	0.0	100.0	0.0	1.0	1.0	3.0	5.0	7.0	13.0	21.0	32.0	51.0	78.0	91.2	100.0	100.0	8.8
								0.0	1.0	0.0	2.0	2.0	2.0	6.0	8.0	11.0	19.0	27.0	13.2	8.8		
62	PA08	PA08-03	3.15	5.00	1.85	0.0	100.0	0.0	2.0	5.0	11.0	14.0	18.0	20.0	25.0	37.0	71.0	90.0	93.8	100.0	100.0	6.2
								0.0	2.0	3.0	6.0	3.0	4.0	2.0	5.0	12.0	34.0	19.0	3.8	6.2		
63	PA08	PA08-04	5.00	6.22	1.22	0.0	100.0	1.0	2.0	4.0	8.0	12.0	17.0	24.0	31.0	43.0	62.0	74.0	80.8	100.0	100.0	19.2
								1.0	1.0	2.0	4.0	4.0	5.0	7.0	7.0	12.0	19.0	12.0	6.8	19.2		
63	PA08	PA08-04	6.22	7.00	0.78	0.0	100.0	1.0	2.0	4.0	8.0	12.0	17.0	24.0	31.0	43.0	62.0	74.0	80.8	100.0	100.0	19.2
								1.0	1.0	2.0	4.0	4.0	5.0	7.0	7.0	12.0	19.0	12.0	6.8	19.2		
64	PA08	PA08-05	7.00	9.00	2.00	1.0	99.0	0.0	1.0	1.0	4.0	5.1	8.1	13.1	22.2	38.4	59.6	73.7	81.4	100.0	100.0	18.6
								0.0	1.0	0.0	3.0	1.0	3.0	5.1	9.1	16.2	21.2	14.1	7.7	18.6		

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuga, %	Täisjäägid sõltel (mm), % kogu proovist												Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %	
			Alates	Kuni				Osajäägid sõltel (mm), % kogu proovist														
								20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063			<0,063
65	PA08	PA08-06	9.00	11.00	2.00	0.0	100.0	1.0	1.0	1.0	2.0	3.0	4.0	8.0	18.0	36.0	60.0	76.0	82.9	100.0	100.0	17.1
								1.0	0.0	0.0	1.0	1.0	1.0	4.0	10.0	18.0	24.0	16.0	6.9	17.1		
66	PA08	PA08-07	11.00	13.00	2.00	0.0	100.0	0.0	1.0	1.0	2.0	3.0	6.0	11.0	24.0	44.0	68.0	85.0	90.6	100.0	100.0	9.4
								0.0	1.0	0.0	1.0	1.0	3.0	5.0	13.0	20.0	24.0	17.0	5.6	9.4		
67	PA08	PA08-08	13.00	14.70	1.70	0.0	100.0	0.0	0.0	1.0	2.0	3.0	6.0	10.0	19.0	33.0	58.0	83.0	89.4	100.0	100.0	10.6
								0.0	0.0	1.0	1.0	1.0	3.0	4.0	9.0	14.0	25.0	25.0	6.4	10.6		

68	K05/PA4	K05-01	0.20	2.20	2.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	6.0	26.0	73.0	95.0	97.5	100.0	100.0	2.5
								0.0	0.0	0.0	0.0	0.0	0.0	1.0	5.0	20.0	47.0	22.0	2.5	2.5		
69	K05/PA4	K05-02	2.20	5.00	2.80	0.0	100.0	0.0	0.0	0.0	0.0	1.0	1.0	3.0	8.0	29.0	74.0	93.0	96.1	100.0	100.0	3.9
								0.0	0.0	0.0	0.0	1.0	0.0	2.0	5.0	21.0	45.0	19.0	3.1	3.9		
70	K05/PA4	PA4-1	5.00	6.70	1.70	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	3.0	8.0	30.0	84.0	91.5	100.0	100.0	8.5
								0.0	0.0	0.0	0.0	0.0	0.0	1.0	2.0	5.0	22.0	54.0	7.5	8.5		
71	K06/PA5	K06-01	0.10	1.30	1.20	11.0	89.0	11.2	19.1	25.8	37.1	41.6	50.6	61.8	75.3	87.6	95.5	97.8	99.1	100.0	100.0	0.9
								11.2	7.9	6.7	11.2	4.5	9.0	11.2	13.5	12.4	7.9	2.2	1.3	0.9		
72	K06/PA5	K06-02	1.30	3.90	2.60	0.0	100.0	4.0	5.0	7.0	10.0	12.0	16.0	23.0	35.0	48.0	68.0	88.0	93.6	100.0	100.0	6.4
								4.0	1.0	2.0	3.0	2.0	4.0	7.0	12.0	13.0	20.0	20.0	5.6	6.4		
73	K08/PA6	K08-01	0.00	2.50	2.50	3.0	97.0	4.1	5.2	8.2	14.4	17.5	22.7	28.9	36.1	44.3	70.1	91.8	95.6	100.0	100.0	4.4
								4.1	1.0	3.1	6.2	3.1	5.2	6.2	7.2	8.2	25.8	21.6	3.8	4.4		
74	K08/PA6	K08-02	2.50	5.00	2.50	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	4.0	57.0	85.2	100.0	100.0	14.8
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	4.0	53.0	28.2	14.8		
75	K08/PA6	PA6-1	5.00	6.50	1.50	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	7.0	50.0	73.8	100.0	100.0	26.2
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	7.0	43.0	23.8	26.2		
76	K09a	K09a-01	0.20	3.00	2.80	7.0	93.0	5.4	8.6	10.8	15.1	16.1	20.4	25.8	36.6	51.6	69.9	81.7	86.7	100.0	100.0	13.3
								5.4	3.2	2.2	4.3	1.1	4.3	5.4	10.8	15.1	18.3	11.8	4.9	13.3		
77	K09b	K09b-01	0.50	1.90	1.40	0.0	100.0	5.0	5.0	5.0	7.0	7.0	8.0	10.0	13.0	25.0	49.0	77.0	88.6	100.0	100.0	11.4
								5.0	0.0	0.0	2.0	0.0	1.0	2.0	3.0	12.0	24.0	28.0	11.6	11.4		
78	K09b	K09b-02	1.90	2.90	1.00	25.0	75.0	6.7	10.7	13.3	17.3	20.0	22.7	26.7	34.7	46.7	62.7	81.3	88.0	100.0	100.0	12.0
								6.7	4.0	2.7	4.0	2.7	2.7	4.0	8.0	12.0	16.0	18.7	6.7	12.0		
79	K09b	K09b-03	2.90	4.70	1.80	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	4.0	57.0	87.3	100.0	100.0	12.7
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	4.0	53.0	30.3	12.7		

Kogu uuringuruumi liivaosise kaalutud keskmised omadused	141.90	1.4	98.6	1.8	3.0	4.4	7.4	8.9	11.8	16.0	23.1	34.4	54.8	77.9	88.3	100.0	100.0	11.7
				1.8	1.3	1.4	3.0	1.5	2.8	4.2	7.1	11.3	20.4	23.1	10.4	11.7		

Ploki 8 liivaosise kaalutud keskmised omadused (veepealne varu)	66.30	2.7	97.3	2.9	4.5	6.2	9.2	10.6	13.3	17.1	23.4	33.0	51.2	77.1	89.5	100.0	100.0	10.5
				2.9	1.6	1.7	3.1	1.4	2.7	3.8	6.3	9.6	18.2	25.9	12.4	10.5		
Ploki 9 liivaosise kaalutud keskmised omadused (veealune plokk)	74.10	0.2	99.8	0.8	1.8	3.0	5.9	7.6	10.6	15.3	23.2	36.2	58.9	79.6	87.9	100.0	100.0	12.1
				0.8	1.0	1.2	3.0	1.6	3.0	4.7	7.9	13.0	22.7	20.7	8.3	12.1		

\*-ga märgitud proovid on jäetud varu arvutuse plokkidest välja  
 ga märgitud proove on kaustatud veealuse varu arvutamisel