

Jrk nr	Uuringu- punkt	Proovi nr	Proovitud intervall		Proovi pikkus, m	Kruusa %	Liiva %	Osajäägid sõeltel, %																	Kokku	Maa- vara liik	
			Sügavus alates, m	Sügavus kuni, m				Loodusliku materjal																			
								Kruus																			
								Liiv																			
								125	80	63	40	31.5	20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063			<0.063
						100.0	-	-	-	-	-	0.0	0.4	0.5	2.0	0.6	1.2	2.8	6.8	29.0	52.2	3.2	0.3	1.0			
18	K10	10-2	1.4	3.6	2.2	19.9	80.1	0.0	0.0	0.0	18.4	1.5	10.3	2.1	3.8	7.0	3.2	5.5	7.9	6.2	10.1	18.4	3.8	0.8	0.9	100	EL
						19.9		0.0	0.0	0.0	92.5	7.5	-	-	-	-	-	-	-	-	-	-	-	-	-		
							80.1	-	-	-	-	-	12.8	2.6	4.8	8.7	4.0	6.9	9.8	7.7	12.6	23.0	4.7	1.0	1.1		
19	K10	10-3	3.6	5.2	1.6	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.3	0.2	0.2	0.1	0.6	40.4	53.0	3.0	2.2	100	EL
						0.0		0.0	0.0	0.0	0.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							100.0	-	-	-	-	-	0.0	0.0	0.0	0.0	0.3	0.2	0.2	0.1	0.6	40.4	53.0	3.0	2.2		
20	K11	11-1	0.6	3.4	2.8	2.6	97.4	0.0	0.0	0.0	0.0	2.6	8.1	3.7	2.7	6.0	2.0	3.1	4.6	7.7	17.3	33.3	5.1	0.6	3.1	100	EL
						2.6		0.0	0.0	0.0	0.0	100.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							97.4	-	-	-	-	-	8.3	3.8	2.8	6.2	2.1	3.2	4.7	7.9	17.7	34.2	5.2	0.6	3.2		
21	K12	12-1	0.6	2.7	2.1	2.2	97.8	0.0	0.0	0.0	0.0	2.2	3.9	1.0	1.3	4.2	2.4	4.8	7.2	17.0	28.4	22.8	2.5	0.5	1.9	100	EL
						2.2		0.0	0.0	0.0	0.0	100.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							97.8	-	-	-	-	-	4.0	1.0	1.3	4.3	2.5	4.9	7.3	17.3	29.1	23.3	2.6	0.5	2.0		
22	K13	13-1	0.0	3.0	3.0	10.8	89.2	0.0	0.0	0.0	5.3	5.5	5.5	3.2	2.1	3.7	1.6	2.7	4.2	8.6	15.1	35.3	6.0	0.3	0.9	100	EL
						10.8		0.0	0.0	0.0	48.9	51.1	-	-	-	-	-	-	-	-	-	-	-	-	-		
							89.2	-	-	-	-	-	6.2	3.6	2.4	4.2	1.8	3.0	4.7	9.6	16.9	39.6	6.7	0.3	1.0		
23	K14	14-1	0.2	1.5	1.3	5.7	94.3	0.0	0.0	0.0	0.0	5.7	3.7	3.5	4.5	7.5	3.9	7.3	9.2	9.8	9.4	21.0	12.5	0.5	1.4	100	EL
						5.7		0.0	0.0	0.0	0.0	100.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							94.3	-	-	-	-	-	3.9	3.7	4.8	8.0	4.2	7.8	9.8	10.4	10.0	22.3	13.3	0.5	1.5		
24	K15	15-1	0.2	1.0	0.8	1.7	98.3	0.0	0.0	0.0	1.7	0.0	4.5	0.3	0.7	1.9	1.2	1.7	1.9	3.2	13.0	50.3	16.4	1.1	1.9	100	EL
						1.7		0.0	0.0	0.0	100.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							98.3	-	-	-	-	-	4.6	0.3	0.8	2.0	1.2	1.8	1.9	3.3	13.2	51.2	16.7	1.1	1.9		
25	K15	15-1	1.4	2.6	1.2	1.7	98.3	0.0	0.0	0.0	1.7	0.0	4.5	0.3	0.7	1.9	1.2	1.7	1.9	3.2	13.0	50.3	16.4	1.1	1.9	100	EL
						1.7		0.0	0.0	0.0	100.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							98.3	-	-	-	-	-	4.6	0.3	0.8	2.0	1.2	1.8	1.9	3.3	13.2	51.2	16.7	1.1	1.9		
26	K15	15-3	2.6	5.0	2.4	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.4	0.2	0.2	0.5	0.6	1.8	21.1	67.3	5.2	2.7	100	EL
						0.0		0.0	0.0	0.0	0.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							100.0	-	-	-	-	-	0.0	0.0	0.0	0.4	0.2	0.2	0.5	0.6	1.8	21.1	67.3	5.2	2.7		
27	PA2	16-1	0.2	4.0	3.8	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.7	1.5	1.0	2.5	1.8	3.4	5.3	6.4	12.4	20.8	24.5	5.5	14.2	100	TL
						0.0		0.0	0.0	0.0	0.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							100.0	-	-	-	-	-	0.7	1.5	1.0	2.5	1.8	3.4	5.3	6.4	12.4	20.8	24.5	5.5	14.2		
28	PA3	17-1	0.2	2.0	1.8	0.0	100.0	0.0	0.0	0.0	0.0	0.0	2.2	0.7	1.1	1.0	0.3	0.4	0.5	1.7	18.9	51.1	5.3	2.8	13.9	100	TL
						0.0		0.0	0.0	0.0	0.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							100.0	-	-	-	-	-	2.2	0.7	1.1	1.0	0.3	0.4	0.5	1.7	18.9	51.1	5.3	2.8	13.9		
29	PA3	17-2	2.0	4.0	2.0	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.4	1.6	1.6	3.4	2.5	5.7	18.2	16.2	10.1	12.3	4.6	3.9	19.4	100	TL
						0.0		0.0	0.0	0.0	0.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							100.0	-	-	-	-	-	0.4	1.6	1.6	3.4	2.5	5.7	18.2	16.2	10.1	12.3	4.6	3.9	19.4		
30	PA3	17-3	4.0	6.2	2.2	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.4	0.3	0.7	2.2	2.4	3.7	28.9	36.3	7.5	17.5	100	TL
						0.0		0.0	0.0	0.0	0.0	0.0	-	-	-	-	-	-	-	-	-	-	-	-	-		
							100.0	-	-	-	-	-	0.0	0.0	0.0	0.4	0.3	0.7	2.2	2.4	3.7	28.9	36.3	7.5	17.5		
				Ploki keskmine		6.0	94.0	0.0	0.7	0.4	2.8	2.0	3.9	1.8	1.7	3.0	1.5	2.5	3.9	5.0	10.1	32.8	20.3	2.2	5.3	100	TL
				Min.		0.0	65.8																	0.3			
				Maks.		34.2	100.0																	20.6			