

LOODUSLIKUST MATERJALIST VÄLJA SÕELUTUD LIIVA OMADUSED

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuaga, %	Täisjäägid sõeltel (mm), % kogu proovist												Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %	
			Osajäägid sõeltel (mm), % kogu proovist																			
			Alates	Kuni				20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063			<0,063
1	K01	K01-01	1.50	2.18	0.68	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.40	34.59	88.70	93.26	100.00	100.0	6.7
								0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.40	34.19	54.11	4.56	6.74		
1	K01	K01-01	2.18	3.00	0.82	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.40	34.59	88.70	93.26	100.00	100.0	6.7
								0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.40	34.19	54.11	4.56	6.74		
2	K02	K02-01	0.55	2.50	1.95	39.3	60.7	17.56	24.35	31.61	41.54	45.25	51.28	58.46	65.04	71.06	79.46	85.32	89.77	100.00	100.0	10.2
								17.56	6.80	7.25	9.94	3.71	6.03	7.17	6.58	6.02	8.39	5.86	4.45	10.23		
3	K02	K02-02	2.50	4.00	1.50	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.19	1.45	80.92	96.84	100.00	100.0	3.2
								0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.19	1.26	79.47	15.92	3.16		
4	K02	K02-03	4.00	4.32	0.32	2.9	97.1	2.37	2.65	2.74	3.29	3.66	4.05	4.81	5.91	7.09	11.04	82.28	96.40	100.00	100.0	3.6
								2.37	0.28	0.10	0.54	0.37	0.39	0.77	1.10	1.18	3.95	71.25	14.12	3.60		
4	K02	K02-03	4.32	5.30	0.98	2.9	97.1	2.37	2.65	2.74	3.29	3.66	4.05	4.81	5.91	7.09	11.04	82.28	96.40	100.00	100.0	3.6
								2.37	0.28	0.10	0.54	0.37	0.39	0.77	1.10	1.18	3.95	71.25	14.12	3.60		
5	K03	K03-01	0.20	3.10	2.90	60.0	40.0	16.87	22.82	28.85	37.58	41.64	48.90	58.51	70.09	81.59	88.80	91.99	94.24	100.00	100.0	5.8
								16.87	5.95	6.03	8.73	4.05	7.26	9.62	11.58	11.50	7.22	3.19	2.25	5.76		
6	K03	K03-02	3.10	5.80	2.70	11.16	88.84	1.24	2.41	4.58	6.82	7.87	9.32	11.79	15.69	22.90	32.33	41.42	57.59	100.00	100.0	42.4
								1.24	1.17	2.17	2.23	1.06	1.44	2.47	3.91	7.21	9.43	9.09	16.17	42.41		
7	K04	K04-01	0.40	1.59	1.19	9.6	90.4	7.95	12.71	16.24	22.75	25.53	29.77	35.94	53.46	74.65	80.73	83.46	87.09	100.00	100.0	12.9
								7.95	4.76	3.53	6.51	2.78	4.23	6.18	17.52	21.18	6.09	2.73	3.63	12.91		
7	K04	K04-01	1.59	2.00	0.41	9.6	90.4	7.95	12.71	16.24	22.75	25.53	29.77	35.94	53.46	74.65	80.73	83.46	87.09	100.00	100.0	12.9
								7.95	4.76	3.53	6.51	2.78	4.23	6.18	17.52	21.18	6.09	2.73	3.63	12.91		
8	K05	K05-01	0.60	2.20	1.60	12.1	87.9	4.85	8.59	11.43	17.33	19.37	23.49	31.15	44.26	55.64	61.74	67.95	74.37	100.00	100.0	25.6
								4.85	3.75	2.83	5.90	2.04	4.12	7.66	13.11	11.38	6.11	6.21	6.41	25.63		
9	K05	K05-02	2.20	2.94	0.74	11.71	88.29	2.75	4.30	5.76	8.38	9.94	12.99	18.63	26.55	33.65	42.92	62.99	81.50	100.00	100.0	18.5
								2.75	1.55	1.46	2.62	1.56	3.05	5.63	7.93	7.10	9.27	20.07	18.51	18.50		
9	K05	K05-02	2.94	3.80	0.86	11.71	88.29	2.75	4.30	5.76	8.38	9.94	12.99	18.63	26.55	33.65	42.92	62.99	81.50	100.00	100.0	18.5
								2.75	1.55	1.46	2.62	1.56	3.05	5.63	7.93	7.10	9.27	20.07	18.51	18.50		
10	K06	K06-01	0.50	0.69	0.19	38.7	61.3	12.15	17.31	22.00	29.60	32.80	38.40	47.01	57.89	64.74	70.04	78.62	86.76	100.00	100.0	13.2
								12.15	5.16	4.70	7.60	3.20	5.59	8.61	10.89	6.84	5.30	8.59	8.14	13.24		
10	K06	K06-01	0.69	3.20	2.51	38.7	61.3	12.15	17.31	22.00	29.60	32.80	38.40	47.01	57.89	64.74	70.04	78.62	86.76	100.00	100.0	13.2
								12.15	5.16	4.70	7.60	3.20	5.59	8.61	10.89	6.84	5.30	8.59	8.14	13.24		
11	K07	K07-01	0.60	2.60	2.00	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.45	3.86	14.81	34.02	57.86	84.07	100.00	100.0	15.9
								0.00	0.00	0.00	0.00	0.00	0.00	0.45	3.41	10.95	19.20	23.84	26.21	15.93		
12	K07	K07-02	2.60	3.10	0.50	1.4	98.6	2.79	5.11	6.85	11.30	13.41	17.45	24.49	33.32	42.52	54.45	68.06	82.12	100.00	100.0	17.9
								2.79	2.31	1.74	4.45	2.11	4.04	7.04	8.82	9.20	11.94	13.60	14.06	17.88		
13	K08	K08-01	0.70	3.00	2.30	12.9	87.1	8.94	16.48	24.70	33.93	36.91	43.24	53.25	70.92	82.34	86.42	89.36	93.71	100.00	100.0	6.3
								8.94	7.54	8.22	9.23	2.98	6.33	10.01	17.67	11.42	4.08	2.94	4.35	6.29		
14	K09	K09-01	0.40	1.50	1.10	3.2	96.8	7.08	9.98	13.51	18.76	21.39	26.16	35.60	51.10	60.43	66.67	72.10	78.81	100.00	100.0	21.2
								7.08	2.89	3.53	5.25	2.63	4.77	9.44	15.51	9.32	6.24	5.43	6.71	21.19		
15	K09	K09-02	1.50	2.51	1.01	0.0	100.0	3.08	4.06	5.94	8.94	10.45	12.70	16.28	21.07	26.47	34.53	45.53	63.13	100.00	100.0	36.9
								3.08	0.98	1.88	3.01	1.51	2.25	3.59	4.78	5.41	8.06	11.00	17.60	36.87		
15	K09	K09-02	2.51	3.40	0.89	0.0	100.0	3.08	4.06	5.94	8.94	10.45	12.70	16.28	21.07	26.47	34.53	45.53	63.13	100.00	100.0	36.9
								3.08	0.98	1.88	3.01	1.51	2.25	3.59	4.78	5.41	8.06	11.00	17.60	36.87		
16	K10	K10-01	0.40	2.46	2.06	24.5	75.5	15.04	20.98	27.11	36.61	40.13	46.17	54.58	70.25	85.07	89.19	90.80	92.74	100.00	100.0	7.3
								15.04	5.95	6.13	9.50	3.52	6.04	8.41	15.67	14.82	4.12	1.61	1.95	7.26		
16	K10	K10-01	2.46	2.55	0.09	24.5	75.5	15.04	20.98	27.11	36.61	40.13	46.17	54.58	70.25	85.07	89.19	90.80	92.74	100.00	100.0	7.3
								15.04	5.95	6.13	9.50	3.52	6.04	8.41	15.67	14.82	4.12	1.61	1.95	7.26		
17	K10	K10-02	2.55	4.50	1.95	13.0	87.0	10.91	15.16	19.14	25.36	28.01	32.37	39.01	54.10	76.24	89.88	93.26	95.23	100.00	100.0	4.8
								10.91	4.25	3.98	6.22	2.65	4.35	6.64	15.09	22.14	13.64	3.37	1.98	4.77		
18	K11	K11-01	0.50	2.70	2.20	30.4	69.6	12.45	17.35	23.46	33.08	38.02	47.63	63.23	76.37	85.08	89.81	91.91	93.74	100.00	100.0	6.3
								12.45	4.90	6.11	9.62	4.94	9.61	15.60	13.15	8.70	4.74	2.10	1.83	6.26		

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuga, %	Täisjäägid sõeltel (mm), % kogu proovist													Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %
			Alates	Kuni				Osajäägid sõeltel (mm), % kogu proovist														
								20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063	<0,063		
19	K12	K12-01	0.80	3.00	2.20	17.1	82.9	17.98	24.69	30.67	39.77	43.30	49.07	55.63	63.59	75.18	87.21	92.05	94.62	100.00	100.0	5.4
								17.98	6.71	5.98	9.10	3.53	5.77	6.56	7.96	11.59	12.03	4.84	2.57	5.38		
20	K13	K13-01	0.50	2.90	2.40	6.1	93.9	6.69	10.33	13.60	19.29	21.41	24.49	28.37	33.15	38.93	48.53	62.42	74.44	100.00	100.0	25.6
								6.69	3.64	3.27	5.69	2.12	3.09	3.88	4.78	5.78	9.61	13.89	12.02	25.56		
21	K15	K15-01	0.30	1.40	1.10	0.0	100.0	0.66	1.31	2.13	5.35	7.57	11.69	20.02	32.03	47.29	59.39	63.67	72.91	100.00	100.0	27.1
								0.66	0.64	0.82	3.22	2.22	4.12	8.34	12.01	15.26	12.10	4.28	9.24	27.09		
22	K15	K15-02	1.40	3.20	1.80	0.0	100.0	0.00	0.00	0.00	0.00	0.00	0.00	0.47	1.00	6.55	46.00	84.29	94.41	100.00	100.0	5.6
								0.00	0.00	0.00	0.00	0.00	0.00	0.47	0.53	5.55	39.45	38.29	10.12	5.59		
23	K16	K16-01	0.40	3.00	2.60	0.0	100.0	0.00	0.14	0.86	1.93	2.63	4.44	10.65	46.49	88.09	95.91	97.33	98.10	100.00	100.0	1.9
								0.00	0.14	0.71	1.07	0.70	1.81	6.20	35.85	41.60	7.82	1.41	0.78	1.90		
24	K16	K16-02	3.00	3.15	0.15	25.6	74.4	12.68	18.41	23.67	31.24	34.33	39.78	50.36	73.37	91.61	95.92	96.87	97.50	100.00	100.0	2.5
								12.68	5.73	5.26	7.58	3.08	5.46	10.58	23.01	18.24	4.31	0.95	0.62	2.50		
24	K16	K16-02	3.15	4.50	1.35	25.6	74.4	12.68	18.41	23.67	31.24	34.33	39.78	50.36	73.37	91.61	95.92	96.87	97.50	100.00	100.0	2.5
								12.68	5.73	5.26	7.58	3.08	5.46	10.58	23.01	18.24	4.31	0.95	0.62	2.50		
25	K19	K19-01	0.30	1.90	1.60	3.2	96.8	8.03	10.88	13.53	17.34	18.70	20.37	22.81	26.58	31.36	37.80	51.67	72.93	100.00	100.0	27.1
								8.03	2.85	2.66	3.80	1.37	1.66	2.45	3.76	4.79	6.43	13.88	21.26	27.07		
26	K20	K20-01	0.30	2.20	1.90	0.0	100.0	0.00	0.22	0.84	1.87	2.27	3.16	5.58	10.01	16.86	28.71	47.14	75.17	100.00	100.0	24.8
								0.00	0.22	0.63	1.03	0.40	0.89	2.43	4.42	6.85	11.85	18.43	28.03	24.83		
27	K20	K20-02	2.20	3.35	1.15	1.9	98.1	0.00	0.86	0.96	1.49	2.02	3.29	6.87	13.74	25.44	45.81	64.88	82.60	100.00	100.0	17.4
								0.00	0.86	0.10	0.53	0.54	1.27	3.58	6.87	11.69	20.38	19.07	17.71	17.40		
27	K20	K20-02	3.35	3.50	0.15	1.9	98.1	0.00	0.86	0.96	1.49	2.02	3.29	6.87	13.74	25.44	45.81	64.88	82.60	100.00	100.0	17.4
								0.00	0.86	0.10	0.53	0.54	1.27	3.58	6.87	11.69	20.38	19.07	17.71	17.40		

Kogu uuringuruumi liivaosise kaalutud keskmised omadused	50.35	14.3	85.7	6.9	10.1	13.3	18.1	20.1	23.7	29.5	39.7	50.6	60.8	75.0	84.3	98.2	100.0	14.5
				6.9	3.1	3.2	4.8	2.0	3.6	5.8	10.2	11.0	10.1	14.2	9.4	13.9		

Ploki 10 (veepealne varu) liivaosise kaalutud keskmised omadused	28.34	13.9	86.1	5.9	8.4	11.1	15.2	16.9	19.9	24.9	35.3	47.2	56.5	71.4	83.1	100.0	100.0	16.9
				5.9	2.6	2.7	4.1	1.7	3.0	5.0	10.4	11.9	9.4	14.8	11.7	16.9		
Ploki 11 (veealune varu) liivaosise kaalutud keskmised omadused	22.01	14.8	85.2	8.4	12.3	16.2	22.2	24.7	29.1	36.0	46.1	56.2	67.6	81.4	88.5	100.0	100.0	11.5
				8.4	3.9	3.9	5.9	2.5	4.4	6.9	10.1	10.0	11.5	13.8	7.1	11.5		

Halliga tähistatud proovid esindavad veealuste osade intervalle (keskmine veetase 67.84 abs m).