

LOODUSLIKUST MATERJALIST VÄLJA SÕELUTUD LIIVA OMADUSED

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuga, %	Täisjäägid sõeltel (mm), % kogu proovist													Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %	
			Alates	Kuni				Osajäägid sõeltel (mm), % kogu proovist															
								20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063	<0,063			
1	PA1	PA1-1	0.30	2.00	1.70	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	10.0	54.0	86.0	91.7	100.0	100.0	8.3	
0.0								0.0	0.0	0.0	0.0	0.0	0.0	1.0	9.0	44.0	32.0	5.7	8.3				
2		PA1-2	2.00	8.00	6.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	7.0	44.0	75.0	84.0	100.0	100.0	16.0		
0.0								0.0	0.0	0.0	0.0	0.0	0.0	1.0	6.0	37.0	31.0	9.0	16.0				
3		PA1-3	8.00	14.00	6.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	2.0	30.0	71.0	83.0	100.0	100.0	17.0		
0.0								0.0	0.0	0.0	0.0	0.0	0.0	2.0	28.0	41.0	12.0	17.0					
4		PA1-4	14.00	20.00	6.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	2.0	8.0	34.6	100.0	100.0	65.4		
0.0								0.0	0.0	0.0	0.0	0.0	0.0	2.0	6.0	26.6	65.4						
PA1 kaalutud keskmine								19.70	0.0	100.0	0.0	0.0	0.0	0.4	3.6	27.8	54.3	69.3	100.0	100.0	30.7		
5	PA2	PA2-1	0.20	1.00	0.80	0.0	100.0	0.0	1.0	1.0	3.0	4.0	6.0	8.0	11.0	17.0	28.0	48.0	63.2	100.0	100.0	36.8	
0.0								1.0	0.0	2.0	1.0	2.0	2.0	3.0	6.0	11.0	20.0	15.2	36.8				
6		PA2-2	1.00	6.00	5.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	2.0	13.0	49.0	76.7	100.0	100.0	23.3	
0.0								0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	11.0	36.0	27.7	23.3				
7		PA2-3	6.00	12.00	6.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	2.0	3.0	5.0	29.0	65.7	100.0	100.0	34.3	
0.0								0.0	0.0	0.0	0.0	1.0	0.0	1.0	1.0	2.0	24.0	36.7	34.3				
8		PA2-4	12.00	17.00	5.00	0.0	100.0	0.0	0.0	0.0	0.0	1.0	0.0	0.0	0.0	1.0	2.0	11.0	22.2	62.8	100.0	62.8	
0.0								0.0	0.0	0.0	0.0	1.0	0.0	1.0	1.0	2.0	10.0	43.0	67.1	100.0			
9		PA2-5	17.00	20.00	3.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	0.0	1.0	8.0	33.0	24.1	32.9	100.0	32.9	
0.0	0.0							0.0	0.0	0.0	0.0	1.0	0.0	0.0	1.0	8.0	33.0	24.1	32.9				
PA2 kaalutud keskmine								19.80	0.0	100.0	0.0	0.0	0.0	0.1	0.3	0.5	0.1	0.7	1.2	5.5	24.9	28.0	38.6
10	PA3	PA3-1	0.70	2.45	1.75	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	5.0	39.0	76.0	88.4	100.0	100.0	11.6	
0.0								0.0	0.0	0.0	0.0	0.0	0.0	1.0	4.0	34.0	37.0	12.4	11.6				
11		PA3-2	2.45	8.00	5.55	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	4.0	12.0	31.8	100.0	100.0	68.2	
0.0								0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	3.0	8.0	19.8	68.2				
PA3 kaalutud keskmine								7.30	0.0	100.0	0.0	0.0	0.0	0.0	0.2	2.0	12.4	27.3	45.4	100.0	100.0	54.6	
12	PA4	PA4-1	0.50	4.20	3.70	0.0	100.0	0.0	0.0	0.0	1.0	1.0	2.0	3.0	5.0	10.0	20.0	35.0	48.1	100.0	100.0	51.9	
0.0								0.0	0.0	1.0	0.0	1.0	1.0	2.0	5.0	10.0	15.0	13.1	51.9				
13		PA4-2	4.20	8.00	3.80	0.0	100.0	0.0	0.0	0.0	1.0	0.0	0.0	0.0	1.0	7.0	53.0	21.0	4.3	12.7	100.0	12.7	
0.0								0.0	0.0	1.0	0.0	0.0	0.0	1.0	7.0	53.0	21.0	4.3	12.7				
14		PA4-3	8.00	14.00	6.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	2.0	7.0	42.0	76.0	86.4	100.0	100.0	13.6	
0.0								0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	5.0	35.0	34.0	10.4	13.6			
15		PA4-4	14.00	20.00	6.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	2.0	22.0	58.0	76.2	100.0	100.0	23.8	
0.0								0.0	0.0	0.0	0.0	0.0	0.0	2.0	20.0	36.0	18.2	23.8					
PA4 kaalutud keskmine								19.50	0.0	100.0	0.0	0.0	0.0	0.4	0.4	0.6	1.1	2.0	6.4	35.6	64.0	76.2	100.0
16	PA5	PA5-1	0.00	3.00	3.00	0.0	100.0	0.0	0.0	0.0	1.0	1.0	2.0	4.0	6.0	10.0	22.0	50.0	73.4	100.0	100.0	26.6	
18	PA6	PA6-1	1.70	5.50	3.80	0.0	100.0	0.0	1.0	1.0	2.0	2.0	3.0	5.0	8.0	16.0	39.0	74.0	83.8	100.0	100.0	16.2	

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuga, %	Täisjäägid sõeltel (mm), % kogu proovist												Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %	
			Osajäägid sõeltel (mm), % kogu proovist																			
			20	16				12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063	<0,063				
19	PA7	PA7-1	0.00	2.00	2.00	24.0	76.0	5.3	6.6	9.2	14.5	17.1	25.0	32.9	42.1	51.3	59.2	67.1	72.1	100.0	100.0	27.9
								5.3	1.3	2.6	5.3	2.6	7.9	7.9	9.2	9.2	7.9	7.9	5.0	27.9		
20		PA7-2	2.00	5.00	3.00	0.0	100.0	5.0	10.0	15.0	24.0	29.0	37.0	46.0	55.0	67.0	79.0	85.0	88.6	100.0	100.0	11.4
								5.0	5.0	5.0	9.0	5.0	8.0	9.0	9.0	12.0	12.0	6.0	3.6	11.4		
21		PA7-3	5.00	8.30	3.30	0.0	100.0	3.0	5.0	8.0	17.0	22.0	31.0	40.0	51.0	65.0	77.0	84.0	87.0	100.0	100.0	13.0
							3.0	2.0	3.0	9.0	5.0	9.0	9.0	11.0	14.0	12.0	7.0	3.0	13.0			
PA7 kaalutud keskmine					8.30	5.8	94.2	4.3	7.2	10.8	18.9	23.4	31.7	40.5	50.3	62.4	73.4	80.3	84.0	100.0	100.0	16.0
22	PA8	PA8-1	0.40	3.50	3.10	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	10.0	41.0	100.0	100.0	59.0
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	9.0	31.0	59.0		
23		PA8-2	3.50	8.00	4.50	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	6.0	30.0	67.0	81.9	100.0	100.0	18.1
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	6.0	24.0	37.0	14.9	18.1		
24		PA8-3	8.00	11.00	3.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	2.0	15.0	52.0	72.9	100.0	100.0	27.1
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	2.0	13.0	37.0	20.9	27.1		
25		PA8-4	11.00	13.00	2.00	0.0	100.0	0.0	0.0	0.0	0.0	1.0	1.0	1.0	1.0	2.0	7.0	22.0	49.0	100.0	100.0	51.0
								0.0	0.0	0.0	0.0	1.0	0.0	0.0	0.0	1.0	5.0	15.0	27.0	51.0		
26		PA8-5	13.00	16.00	3.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	2.0	9.0	27.9	100.0	100.0	72.1
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	2.0	7.0	18.9	72.1		
27		PA8-6	16.00	19.20	3.20	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	2.0	6.0	17.0	36.2	100.0	100.0	63.8
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	4.0	11.0	19.2	63.8		
PA8 kaalutud keskmine					18.80	0.0	100.0	0.0	0.0	0.0	0.0	0.1	0.1	0.1	0.3	2.5	11.8	32.7	53.8	100.0	100.0	46.2
28	PA10	PA10-1	0.45	1.10	0.65	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	3.0	14.0	60.0	89.0	93.9	100.0	100.0	6.1
								0.0	0.0	0.0	0.0	0.0	0.0	1.0	2.0	11.0	46.0	29.0	4.9	6.1		
30	PA13	PA13-1	0.30	5.20	4.90	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	4.0	17.0	51.0	78.0	100.0	100.0	22.0
								0.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	3.0	13.0	34.0	27.0	22.0		
31		PA13-2	5.20	6.60	1.40	0.0	100.0	0.0	0.0	0.0	2.0	3.0	4.0	7.0	11.0	15.0	21.0	35.0	54.2	100.0	100.0	45.8
								0.0	0.0	0.0	2.0	1.0	1.0	3.0	4.0	4.0	6.0	14.0	19.2	45.8		
32		PA13-3	6.60	12.00	5.40	0.0	100.0	0.0	0.0	0.0	1.0	1.0	1.0	1.0	2.0	3.0	6.0	20.0	39.1	100.0	100.0	60.9
							0.0	0.0	0.0	1.0	0.0	0.0	0.0	1.0	1.0	3.0	14.0	19.1	60.9			
33	PA13-4	12.00	16.00	4.00	0.0	100.0	0.0	0.0	0.0	0.0	1.0	1.0	1.0	1.0	2.0	8.0	34.0	59.5	100.0	100.0	40.5	
							0.0	0.0	0.0	0.0	1.0	0.0	0.0	0.0	1.0	6.0	26.0	25.5	40.5			
PA13 kaalutud keskmine					16.35	0.0	100.0	0.0	0.0	0.0	0.5	0.8	0.9	1.5	2.3	4.5	13.2	36.7	59.2	100.0	100.0	40.8
34	PA14	PA14-1	0.60	3.00	2.40	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	4.0	17.0	50.0	75.6	100.0	100.0	24.4
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	3.0	13.0	33.0	25.6	24.4		
35		PA14-2	3.00	6.00	3.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	7.0	29.0	29.1	33.9	100.0	33.9
PA14 kaalutud keskmine					5.40	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.4	2.3	12.0	42.8	70.3	100.0	100.0	29.7

Jrk nr	Kaeve nr	Proovi nr	Proovitud intervall, m		Proovi pikkus, m	Kruus, %	Liiv koos savi ja tolmuga, %	Täisjäägid sõeltel (mm), % kogu proovist												Kokku, %	Savi- ja tolmusisaldus (<0.063 mm), %		
			Osajäägid sõeltel (mm), % kogu proovist																				
			20	16				12.5	8	6.3	4	2	1	0.5	0.25	0.125	0.063	<0,063					
36	PA15	PA15-1	0.40	2.00	1.60	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	3.0	11.0	34.0	59.0	75.1	100.0	100.0	24.9	
								0.0	0.0	0.0	0.0	0.0	0.0	1.0	2.0	8.0	23.0	25.0	16.1	24.9			
37		PA15-2	2.00	8.00	6.00	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	1.0	17.0	56.0	73.2	100.0	100.0	26.8		
								0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.0	0.0	16.0	39.0	17.2			26.8	
PA15 kaalutud keskmine					7.60	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.2	1.4	3.1	20.6	56.6	73.6	100.0	100.0	26.4	
2009. aasta puuraukude andmed																							
38	PA-2	10	0.10	1.90	1.80	6.8	93.2	8.2	12.0	16.2	22.5	25.3	30.2	37.4	47.7	65.0	79.4	85.6	88.3	100.0	100.0	11.7	
								8.2	3.8	4.2	6.4	2.7	5.0	7.2	10.3	17.3	14.4	6.2	2.7	11.7			
39		11	1.90	4.50	2.60	1.0	99.0	1.9	3.9	6.1	10.1	12.2	16.5	23.8	35.2	56.0	75.6	83.8	87.0	100.0	100.0	13.0	
								1.9	2.0	2.2	4.0	2.1	4.3	7.4	11.4	20.8	19.6	8.2	3.2	13.0			
40		12	4.50	7.50	3.00	0.0	100.0	0.0	0.0	0.0	0.3	0.6	1.1	1.6	2.4	8.7	40.5	86.0	91.2	100.0	100.0	8.8	
								0.0	0.0	0.0	0.3	0.3	0.5	0.5	0.9	6.3	31.8	45.5	5.2	8.8			
41		13	7.50	10.50	3.00	0.0	100.0	0.0	0.0	0.0	0.5	1.0	1.7	2.2	4.0	15.1	44.0	74.5	83.1	100.0	100.0	16.9	
								0.0	0.0	0.0	0.5	0.5	0.7	0.5	1.8	11.1	28.9	30.6	8.6	16.9			
42		14	10.50	12.90	2.40	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.1	0.5	4.1	20.6	54.9	73.2	100.0	100.0	26.8	
								0.0	0.0	0.0	0.0	0.0	0.0	0.1	0.4	3.6	16.5	34.3	18.3	26.8			
43		15	12.90	15.80	2.90	0.0	100.0	0.0	0.0	0.0	0.2	0.3	0.6	0.9	1.4	4.7	20.5	55.8	73.8	100.0	100.0	26.2	
								0.0	0.0	0.0	0.2	0.2	0.3	0.3	0.5	3.3	15.7	35.4	18.0	26.2			
PA-2 kaalutud keskmine					15.70	0.9	99.1	1.2	2.0	2.9	4.4	5.3	6.8	9.1	12.9	22.8	44.7	73.1	82.7	100.0	100.0	17.3	
44	PA-10	62	0.10	2.20	2.10	8.2	91.8	1.1	2.5	4.0	6.6	7.8	10.0	13.3	17.4	24.8	36.4	55.0	66.6	100.0	100.0	33.4	
								1.1	1.4	1.6	2.5	1.2	2.2	3.3	4.1	7.4	11.6	18.6	11.6	33.4			
45		63	2.20	4.70	2.50	0.0	100.0	0.0	0.0	0.0	0.0	0.0	0.0	0.1	0.3	0.9	4.1	28.7	53.9	100.0	100.0	46.1	
								0.0	0.0	0.0	0.0	0.0	0.0	0.1	0.2	0.6	3.1	24.6	25.2	46.1			
46		64	4.70	7.10	2.40	0.0	100.0	0.0	0.0	0.0	0.0	0.1	0.1	0.3	0.5	1.1	2.9	18.4	37.2	100.0	100.0	62.8	
								0.0	0.0	0.0	0.0	0.0	0.1	0.1	0.3	0.5	1.8	15.5	18.9	62.8			
47		65	7.10	10.80	3.70	0.0	100.0	0.0	0.0	0.0	0.9	1.9	3.3	4.5	15.3	48.3	78.4	87.3	90.0	100.0	100.0	10.0	
								0.0	0.0	0.0	0.9	1.0	1.3	1.3	10.7	33.0	30.0	8.9	2.7	10.0			
48		66	10.80	14.30	3.50	0.0	100.0	0.0	0.0	0.0	1.1	2.3	3.8	4.8	10.8	37.0	73.3	86.6	89.3	100.0	100.0	10.7	
								0.0	0.0	0.0	1.1	1.2	1.5	1.0	6.0	26.2	36.3	13.3	2.7	10.7			
49		67	14.30	17.80	3.50	0.0	100.0	0.0	0.0	0.0	4.6	9.5	15.3	19.1	28.0	52.1	79.3	88.8	91.2	100.0	100.0	8.8	
								0.0	0.0	0.0	4.6	4.9	5.9	3.7	8.9	24.1	27.2	9.5	2.4	8.8			
50		68	17.80	21.20	3.40	0.0	100.0	0.0	0.0	0.0	1.6	3.3	5.6	9.0	26.0	62.5	85.4	91.2	93.2	100.0	100.0	6.8	
								0.0	0.0	0.0	1.6	1.7	2.3	3.4	16.9	36.5	22.9	5.9	1.9	6.8			
PA-10 kaalutud keskmine					21.10	0.8	99.2	0.1	0.2	0.4	2.0	3.6	5.7	7.6	15.1	36.0	57.2	70.1	78.0	100.0	100.0	22.0	
Kogu maavara kaalutud keskmised omadused					167.00	0.5	99.5	0.3	0.6	0.9	1.8	2.4	3.3	4.4	6.7	12.9	29.5	52.9	69.2	100.0	100.0	30.8	
								0.3	0.3	0.3	0.9	0.6	1.0	1.1	2.3	6.2	16.6	23.4	16.3	30.8			