

LOODUSLIKU MATERJALI GRANULOMEETRILISE KOOSTISE TABEL (EVS-EN 933-1)

Uuringu- augu nr	Proovi		Kruus	Liiv	Savi, tolm, ≤0,063 mm, %	Läbind, %																Maavara	
	nr	pikkus, m	>31.5 mm, %	31.5- 0,063 mm, %		125	80	63	40	31.5	20	16	12.5	8	6.3	4	2	1	0.5	0.25	0.125		0.063
K-1	K 1-1	0.7	13.1	80.1	6.8	100	100	100	88	87	85	83	81	78	76	73	70	66	59	40	20	6.8	TL
	K 1-2	0.8	0.0	82.0	18.0	100	100	100	100	100	100	100	100	100	100	99	99	98	96	89	56	18.0	TL
K-2	K 2-1	1.8	46.6	49.1	4.3	100	100	95	63	53	38	33	29	26	24	22	20	19	16	12	7	4.3	EK
K-3	K 3-1	2.2	7.5	85.5	7.0	100	100	100	95	93	86	81	76	67	62	52	43	31	19	13	10	7.0	TL
K-4	K 4-2	4.1	0.0	93.0	7.0	100	100	100	100	100	100	100	100	100	100	100	100	100	98	65	23	7.0	TL
K-5	K 5-1	2.8	0.4	81.3	18.3	100	100	100	100	100	94	92	89	86	84	81	78	73	67	59	42	18.3	TL
K-6	K 6-2	1.6	0.0	80.6	19.4	100	100	100	100	100	100	100	100	100	100	100	100	100	99	86	48	19.4	TL
	K 6-3	1.6	10.4	73.7	15.9	100	100	100	92	90	81	79	77	74	72	70	68	65	59	47	33	15.9	TL
K-7	K 7-2	1.6	4.0	89.7	6.3	100	100	100	98	96	93	89	85	77	71	63	56	43	27	17	12	6.3	TL
K-8	K 8-1	0.9	37.5	61.1	1.4	100	100	89	69	63	53	49	44	37	34	29	24	17	8	4	2	1.4	EK
	K 8-2	1.0	0.0	96.6	3.4	100	100	100	100	100	100	100	100	99	99	97	93	83	61	26	9	3.4	EL
	K 8-3	2.1	0.0	54.3	45.7	100	100	100	100	100	100	100	100	100	100	100	100	100	99	98	87	45.7	TL
K-9	K 9-2	2.3	0.0	90.3	9.7	100	100	100	100	100	98	98	96	93	91	86	80	63	42	26	16	9.7	TL
UURINGURUUM, PLOKID 4 ja 5 aT																							
Min			0.0	49.1	1.4	100.0	100.0	89.0	63.2	53.4	38.0	32.8	29.3	25.7	24.2	21.7	20.4	17.1	8.1	4.1	2.3	1.4	
Max			46.6	96.6	45.7	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	99.9	99.4	98.2	86.7	45.7	
Kaalutud keskmine			7.1	79.6	13.3	100.0	100.0	99.2	94.5	92.9	88.9	87.2	85.3	82.3	80.7	77.6	74.6	69.2	61.6	47.5	29.0	13.3	TL